

DUREMAX[®] GPE ZP

General Purpose Epoxy Zinc Phosphate Primer

PC 215

- FEATURES**
- EXCELLENT DURABILITY IN A WIDE RANGE OF ENVIRONMENTS
 - EASE OF APPLICATION - SPRAY, BRUSH, ROLLER
 - INHIBITIVE CORROSION PROTECTION
 - GOOD ABRASION RESISTANCE
 - HIGH BUILD FORMULATION PROVIDES SUPERIOR EDGE PROTECTION COMPARED WITH CONVENTIONAL ZINC PHOSPHATE EPOXIES

USES DUREMAX[®] GPE ZP has been locally developed specially for Australasian conditions using the latest epoxy technology. It is a general-purpose epoxy primer enhanced with zinc phosphate pigment for inhibitive corrosion protection on mild steel. DUREMAX[®] GPE ZP is a high performance coating for the protection of structures exposed to severe environments such as chemical plants, offshore platforms, refineries, ship loaders and coal wash plants.

- SPECIFICATIONS**
- APAS 2971 V11: assessed and confirmed to meet all requirements on specific certified products
 - AS/NZS 3750.13
- Refer to a Dulux Protective Coatings Consultant for details of the system.

RESISTANCE GUIDE

WEATHERABILITY	Will yellow with time and chalk on exterior exposure. Neither yellowing nor chalking detracts from the protective properties of the coating. Use a weatherable topcoat if required for appearance.	SOLVENTS	Resists splash and spillage of most hydrocarbon solvents, refined petroleum products and most common alcohols
HEAT RESISTANCE	Up to 120°C dry heat	WATER	Excellent resistance to fresh and salt water but not suitable for immersion
SALTS	Excellent resistance to neutral and alkaline salts	ALKALIS	Suitable for splash and spillage of strong alkali
ACIDS	Suitable for splash and spillage of mild acids	ABRASION	Good when fully cured

TYPICAL PROPERTIES AND APPLICATION DATA (STANDARD HARDENER)

CLASSIFICATION	Anticorrosive epoxy primer	APPLICATION CONDITIONS			
FINISH	Semi Gloss		Min	Max	
COLOUR	Light-mid grey (approximate match to AS2700 N33 Lightbox Grey)	Air Temp.	10°C	40°C	
COMPONENTS	Two	Substrate Temp.	10°C	40°C	
VOLUME SOLIDS	72±2%	Relative Humidity		85%	
VOC LEVEL	<330 g/L	Concrete Moisture		<6%	
FLASH POINT	4°C	COATING THICKNESS (MICRONS)			
POT LIFE	3 – 4 hours (4 litre kit, 25°C)		Min	Max	Recommended
MIXING RATIO V/V	Part A : 4 Part B : 1	Wet film per coat (µm)	140	280	175
THINNER	920-08925 Dulux [®] Epoxy Thinner	Dry film per coat (µm)	100	200	125
THINNER	920-81942 Dulux [®] Duthin [®] 450 Cold Weather Thinner	SUITABLE SUBSTRATES	Blast cleaned steel and galvanised steel		
PRODUCT CODE	780-52033 Grey 976-84577 Standard Hardener 976-84741 Fast Cure Hardener 976-84892 Quickturn [®] Hardener	PRIMERS	Not applicable		
		TOPCOATS	Most Dulux [®] two pack topcoats		
		APPLICATION METHODS	Brush, roller, conventional, airless spray or air assisted spray		

DRYING CHARACTERISTICS AT 125 µm DRY FILM THICKNESS* (STANDARD HARDENER)

Temperature	Humidity	Touch	Handle	Full Cure	OVERCOAT	
					Min	Max ¹
10° C	50%	16 Hours	28 Hours	7 Days	28 Hours	4 Weeks
15° C	50%	12 Hours	20 Hours	7 Days	20 Hours	4 Weeks
25° C	50%	4 Hours	10 Hours	7 Days	8 Hours	4 Weeks

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹If the maximum overcoat interval is exceeded then the surface **MUST** be abraded to ensure maximum intercoat adhesion.

SPREADING RATE

with Standard Hardener
assuming no losses

5.7 square metres per litre equals 125 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

DUREMAX® GPE ZP

FAST CURE HARDENER

COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	135	265	165
Dry film per coat (µm)	100	200	125
SOLIDS BY VOLUME	76±2%		
VOC LEVEL	<300 g/L		
POT LIFE	2 hours (4 litre kit, 25°C)		

APPLICATION CONDITIONS

	Min	Max
Air Temperature	5°C	40°C
Substrate Surface Temperature	5°C	40°C
Relative Humidity		85%
Concrete Moisture Content		<6%

DRYING CHARACTERISTICS AT 125 µm DRY FILM THICKNESS* (FAST CURE HARDENER)

OVERCOAT

Temperature	Humidity	Touch	Handle	Full Cure	Min	Max ¹
5° C	50%	9 Hours	18 Hours	7 Days	18 Hours	4 Weeks
10° C	50%	6 Hours	14 Hours	7 Days	14 Hours	4 Weeks
15° C	50%	5 Hours	10 Hours	7 Days	10 Hours	4 Weeks
25° C	50%	2.5 Hours	6 Hours	7 Days	6 Hours	4 Weeks

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying

¹ If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level.

SPREADING RATE

with Fast Cure Hardener
assuming no losses

6.0 square metres per litre equals 125 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

QUICKTURN® HARDENER

COATING THICKNESS (MICRONS)

	Min	Max	Recommended
Wet film per coat (µm)	140	275	170
Dry film per coat (µm)	100	200	125
SOLIDS BY VOLUME	74±2%		
VOC LEVEL	<310 g/L		
POT LIFE	90 Minutes (4 litre kit, 25°C)		

APPLICATION CONDITIONS

	Min	Max
Air Temperature	5°C	35°C
Substrate Surface Temperature	5°C	35°C
Relative Humidity		85%
Concrete Moisture Content		<6%

DRYING CHARACTERISTICS AT 125 µm DRY FILM THICKNESS* (QUICKTURN® HARDENER)

OVERCOAT

Temperature	Humidity	Touch	Handle	Full Cure	Min	Max ¹
5° C	50%	7 Hours	14 Hours	7 Days	14 Hours	4 Weeks
10° C	50%	5 Hours	9 Hours	7 Days	9 Hours	4 Weeks
15° C	50%	3 Hours	5 Hours	7 Days	5 Hours	4 Weeks
25° C	50%	90 Minutes	3 Hours	7 Days	3 Hours	4 Weeks

*These figures are a guide only, as ventilation, film thickness, humidity, thinning and other factors will influence the rate of drying.

¹ If the maximum overcoat interval is exceeded then the surface MUST be abraded to ensure maximum intercoat adhesion.

Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level.

SPREADING RATE

with Quickturn® Hardener
assuming no losses

5.8 square metres per litre equals 125 µm dry film thickness

NOTE: Practical spreading rates will vary depending on such factors as application method, ambient conditions, surface porosity and roughness.

DUREMAX® GPE ZP

TYPICAL SYSTEMS

This is a guide only and not to be used as a specification. Your specific project needs must be discussed with a Dulux Protective Coatings Consultant.

SURFACE	ENVIRONMENT	PREPARATION GUIDE	SYSTEM	DFT (µm)
STEEL – NEW	Moderate – High (AS2312.1 Cat C4)	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat Duremax® GPE ZP 2 nd Coat Duremax® GPE MIO 3 rd Coat Duremax® GPE MIO	125 µm 125 µm 125 µm
STEEL – NEW	Mild – Moderate (AS2312.1 Cat 3)	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat Duremax® GPE ZP 2 nd Coat Weathermax® HBR	125 µm 100 µm
STEEL – NEW	Interior	Abrasive blast clean AS1627.4 Class 2.5	1 st Coat Duremax® GPE ZP 2 nd Coat Duremax® GPE	125 µm 125 µm

NOTE: If the application is by brush or roller, additional coats will be necessary to achieve the minimum DFT and full opacity

SURFACE PREPARATION	Steel: Round off all rough welds, sharp edges and remove weld spatter. Remove grease, oil and other contaminants in accordance with AS1627.1. Degrease with Gamlen CA 1 (a free-rinsing, alkaline detergent) according to the manufacturer's written instructions and all safety warnings. Abrasive blast clean to a minimum of AS1627.4 Class 2.5.
APPLICATION	Mix each can thoroughly using a power mixer until the contents are uniform. Mix the contents of both packs together thoroughly using a power mixer and allow to stand for 10 minutes. Remix thoroughly before application.
BRUSH/ROLLER	Apply even coats of the mixed material to the prepared surface. When brushing and rolling additional coats may be required to attain the specified thickness.
CONVENTIONAL SPRAY	Thinning is not normally required, however a small amount (5% or less by volume) of Dulux® Epoxy Thinner (920-08925) or Duthin® 450 (920-81942) can be added. Typical Set-up Graco AirPro 1.8mm (239543) Pressure at Triton 308: 70-100 kPa (10-15 p.s.i.) Pressure at Gun: 380-415 kPa (55-60 p.s.i.)
AIRLESS SPRAY	Standard airless spray equipment such as Graco Xtreme 45:1 with a fluid tip of 17-21 thou (0.43- 0.53mm) and an air supply capable of delivering 550-690 kPa (80 -100 psi) at the pump. Thinning is not usually required but up to 50ml/litre of Dulux® Epoxy Thinner (920-08925) or Duthin® 450 (920-81942) may be added to aid application.
PRECAUTIONS	This is an industrial product designed for use by experienced Protective Coating applicators. Where conditions may require variation from the recommendations on this Product Data Sheet contact your nearest Dulux® Consultant for advice prior to painting. Do not apply in conditions outside the parameters stated in this document without the express written consent of Dulux® Australia. Freshly mixed material must not be added to material that has been mixed for some time. Do not apply at temperatures below 10°C when using Standard hardener or 5°C when using Fast Cure or Quickturn® hardener. In cold conditions. Where a fast thinner is required, use Duthin® 450 (920-81942). Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dewpoint. DO NOT USE on galvanised steel when using Fast Cure hardener as delamination can occur. Use of fast or low temperature hardeners may result in increased yellowing and a reduction of gloss level.
CLEAN UP	Clean all equipment with Dulux® Epoxy Thinner (920-08925) or Duthin® 450 (920-81942) immediately after use.
OVERCOATING	Degrease with Gamlen CA 1 according to the data sheet. Test adhesion of existing coating by standard cross hatch adhesion test. If the coating fails, remove it. High-pressure water wash at 8.3 to 10.3 MPa (1,200-1,500 p.s.i.) to remove chalk and dust. Abrade surface to provide a good key for the new coating. Epoxies must be abraded if recoated outside the recoat window.
SAFETY PRECAUTIONS	Read Data Sheet, SAFETY DATA SHEET and any precautions on container labels. SAFETY DATA SHEET is available from Customer Service (13 23 77) or www.duluxprotectivecoatings.com.au
STORAGE	Store as required for a flammable liquid Class 3 in a bunded area under cover. Store in well-ventilated area away from sources of heat or ignition. Keep containers closed at all times.
HANDLING	As with any chemical, ingestion, inhalation and prolonged or repeated skin contact should be avoided by good occupational work practice. Eye protection approved to AS1337 should be worn where there is a risk of splashes entering the eyes. Always wash hands before smoking, eating, drinking or using the toilet.
USING	Use with good ventilation and avoid inhalation of spray mists and fumes. If risk of inhalation of spray mists exists, wear combined organic vapour/particulate respirator. When spraying, users must comply with their respective State Spray Painting Regulations.
FLAMMABILITY	This product is flammable. All sources of ignition must be eliminated in, or near the working area. DO NOT SMOKE. Fight fire with foam, CO ₂ or dry chemical powder. On burning will emit toxic fumes.
WELDING	Avoid inhalation of fumes if welding surfaces coated with this paint. Grind off coating before welding.

COMPANY INFORMATION

Dulux Protective Coatings a division of	
DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton 3168 A.B.N. 67 000 049 427	DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road, Lower Hutt, NZ A.B.N. 55 133 404 118

PACKAGING, TRANSPORT AND STORAGE

PACKAGING	Available in 4 litre and 15 litre packs
TRANSPORTATION WEIGHT	1.6 kg/litre (Average of components)
DANGEROUS GOODS	Part A: Class 3 UN 1263 Part B: Class 8,3 UN 2733 (Standard)

Dulux, Duthin, Duremax, Quickturn, Weathermax and Zincode are registered trademarks of DuluxGroup (Australia) Pty Ltd.

Any advice, recommendation, information, assistance or service provided by Dulux Australia in relation to goods manufactured by it or their use and application is given in good faith and is believed by Dulux to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by Dulux is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Dulux by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Products can be expected to perform as indicated in this sheet so long as applications and application procedures are as recommended. Specific advice should be sought from Dulux for application in highly corrosive areas and for large projects to ensure proper performance.